Ocono

France

INOXX PU FOOD ASP 0,4

Very light weight and highly flexible spiral hose made of Polyurethane, antistatic and food grade



Applications food production & -conveying, pharmaceutical production, textile fiber extraction, extraction systems, extractions arms

Structure Polyether-Polyurethane, transparent, steel wire / stainless steel wire

Temperature -40°C up to 100°C, short term up to 125°C

Properties excellent flexibility, compressible, good abrasion resistance, permanently antistatic (R < 10^9 Ohm), hydrolysis & microbe resistant

Norms certified according to Food EU Directive (EC) No. 1935/2004 & Regulation (EC) No. 10/2011 for E | TRBS 2153, TRGS 727, ATEX 2014/34/EU / pneumatic transport of combustible dusts (inside: zone 20, 21, 22), ATEX 2014/34/EU / use in zones 1 & 2, ATEX 2014/34/EU / use in zone 0, ATEX 2014/34/EU / aspiration (no zone or inside: zone 22) | FDA standard 21 CFR 177.2600 & 178.2010 | manufacturing process according to GMP EC 2023/2006





made in Germany

Inner Diameter (mm)	Outer Diameter (mm)	Wall Thickness (mm)	Bending Radius (mm)	Max. Operating Pressure (bar)	Vacuum Max. (bar)	Total Weight per Piece (kg)	Length (m)	Article Number
25	29,00	0,40	15	0,65	0,30	1,42	10	ND52602500K
25	29,00	0,40	15	0,65	0,30	2,12	15	ND52602500M
38	42,00	0,40	22	0,50	0,25	2,08	10	ND52603800K
38	42,00	0,40	22	0,50	0,25	3,12	15	ND52603800M
40	44,00	0,40	24	0,50	0,25	2,09	10	ND52604000K
51	55,00	0,40	31	0,45	0,20	2,61	10	ND52605100K
51	55,00	0,40	31	0,45	0,20	3,92	15	ND52605100M
60	64,00	0,40	36	0,40	0,16	3,04	10	ND52606000K
60	64,00	0,40	36	0,40	0,16	4,56	15	ND52606000M
63	67,00	0,40	37	0,38	0,15	3,18	10	ND52606300K
63	67,00	0,40	37	0,38	0,15	4,78	15	ND52606300M
76	80,00	0,40	45	0,30	0,12	3,85	10	ND52607600K
76	80,00	0,40	45	0,30	0,12	5,78	15	ND52607600M
80	84,00	0,40	48	0,28	0,10	3,99	10	ND52608000K
80	84,00	0,40	48	0,28	0,10	5,99	15	ND52608000M
102	107,00	0,40	60	0,20	0,09	7,57	15	ND52610200M
102	107,00	0,40	60	0,20	0,09	5,04	10	ND52610200K
120	125,00	0,40	72	0,20	0,08	6,90	10	ND52612000K
120	125,00	0,40	72	0,20	0,08	10,36	15	ND52612000M
127	132,00	0,40	75	0,18	0,07	6,24	10	ND52612700K
127	132,00	0,40	75	0,18	0,07	9,36	15	ND52612700M
152	157,00	0,40	92	0,09	0,06	7,44	10	ND52615200K

Ocono France SARL | 30 Chemin de Fortuneau | 26200 Montélimar | France | T +33 475 017575 | france@ocono.com

All technical data, measured at 23°C, are general orientation values and are subject to production-related tolerances. Max. operating pressures apply only for short periods. Technical changes and color deviations are subject to change. Other versions are available upon request.

Date: 25.11.2026

Inner Diameter (mm)	Outer Diameter (mm)	Wall Thickness (mm)	Bending Radius (mm)	Max. Operating Pressure (bar)	Vacuum Max. (bar)	Total Weight per Piece (kg)	Length (m)	Article Number
152	157,00	0,40	92	0,09	0,06	11,15	15	ND52615200M
180	185,00	0,40	108	0,09	0,06	8,77	10	ND52618000K
203	209,00	0,40	123	0,07	0,05	0,00	10	ND52620300K
203	209,00	0,40	123	0,07	0,05	0,00	15	ND52620300M
250	256,00	0,40	150	0,05	0,04	13,06	10	ND52625000K

Ocono France SARL | 30 Chemin de Fortuneau | 26200 Montélimar | France | T +33 475 017575 | france@ocono.com

All technical data, measured at 23°C, are general orientation values and are subject to production-related tolerances. Max. operating pressures apply only for short periods. Technical changes and color deviations are subject to change. Other versions are available upon request.
Date: 25.11.2026